

## Technical data sheet

**Product:** PrimaCover Glass

**PRIMACOVER**

<b>Article nr.</b>	:	900020	900578	900611
<b>EANnr.</b>	:	8719439000209	8719439005785	8719439006119
<b>Dimensions</b>				
<b>length</b>	:	100m	100m	100m
<b>width</b>	:	0.5m	1m	0.5m
<b>Colour</b>	:	Blue-transparent	Colourless	Blue-transparent

### Technical data

<b>Material</b>	:	LDPE (polyethylene)	
<b>Thickness</b>	:	50 µm +/- 10%	
<b>Density</b>	:	0,922	
<b>Weight per m<sup>2</sup></b>	:	46 gr +/- 10%	
<b>Adhesive</b>	:	Acrylic	
<b>Elongation at break (%)</b>			
<b>MD</b>	:	> 200%	
<b>CD</b>	:	> 400%	
<b>Adhesive strength on glass</b>	:	> 80cN/cm	AFERA 4001

### Usage

The film must be applied to dry and clean surfaces.  
 The application must be done without grease, water or excessive stretching of the film.  
 The film must be removed again within 4 weeks.

### Application

Glass protection film for indoor and outdoor use.

### Storage

Temperature between +10°C and +30°C.  
 Relative humidity: 50%  
 6 months in original packaging. The film must be processed during this time.

Proper and thus successful processing of the product is not within our control. A guarantee can therefore only be given for the quality of the product and not for its processing. It is the responsibility of the user to determine the suitability of our products for their purpose.

The above data are approximate values obtained in our laboratories and at external testing institutes. They may also show slight deviations due to variations in test equipment.

The right to make changes without prior notice is reserved.